































		WAR THE TAXABLE PARTY OF THE PA	Market Committee
Caractéristiques	Kenndaten	Characteristics	ALC:
Matière: céramique	Keramik-Werkstoff	Material: ceremics	Al <sub>2</sub> O <sub>3</sub>
Résistivité	Spezifischer elektrischer Widerstand	Resistivity	> 10" \O / cm
	Durchschlagsfestigkeit	Dielectric strength	10 kV / mm
Rigidité diélectrique	Wärmewiderstand	Thermal resistance	(AOS 3) 0,3 K/W
Résistance thermique	Wärmeleitfähigkeit	Thermal conductivity	25 W / m K
Conductibilité thermique	Linearer Ausdehnungskoeffizient	Coefficient of linear expansion	~8-104/K
Coefficient de dilatation linéairs	The state of the s	Dielectric constant	9
Constante diélectrique	Dielektrizitätskonstante	7 Planess	0.05 mm p. 25 mm
/7 Plandité	// Ebenhoit	77 11011000	