



**GENERAL PRODUCT SPECIFICATION**

<b>Item No.</b>	<b>CH30DP</b>
-----------------	---------------

<b>Date</b>	16-6-2017	<b>Replaces</b>	12-09-13	<b>No. Pages</b>	1
-------------	-----------	-----------------	----------	------------------	---

**Product Description:**

<b>Style</b>	Blanket Roll; high strength perforation down the middle for the 15” wide dimension, & cross-wise for the 15” long dimension.
<b>Item Size (each)</b>	76cm x 46m <b>(240 pads per roll)</b>
<b>Color</b>	Yellow
<b>Composition</b>	100% Polypropylene
<b>Structure</b>	A 3-ply non-woven mat of randomly oriented meltblown micro-fibers [2-10 micron diameters] One side having a Yellow lint & abrasion resistant spunbond cover-stock (non-woven, continuous filaments randomly oriented and thermally point bonded [15-30 micron diameters]). Other side is meltblown Coverstock The (3) plies are secured together with bonded dimpling.
<b>Technology</b>	Spunbond , Meltblown & Meltblown Coverstock
<b>Absorbency</b>	Universal ( <b>Hydrophilic</b> + Oleophilic)
<b>Bonding</b>	Bonded (staggered pattern) + Mechanical entanglement

<b>Intended Application</b>	Abrasion Resistant, Lint Resistant, & Chemical Resistant Sorbent for Oil or Solvent Base Liquids
-----------------------------	--

<b>Absorbency Capacity</b>	147l per bale (saturated; medium viscosity-12.5x)
----------------------------	---

**Packaging Description:**

Package configuration	Case	Pkg. Weight	11.4kg (10,1kg)
Items per Package	1 Bale / Case	Pkg. Dimensions	45 cm x 45 cm x 80 cm (H)
Container type	Carton		

**Physical Properties:**

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002A	G/M2	290	29
Caliper	SPCTM-003A	mils	175	17
Absorbency ** (med. Oil)	SPCTM-004B	gL/gS	12.5	2
Tensile Strength	SPCTM-007	lbs	18	2
Color	Visual	-----	Yellow	per standard

The above properties are “nominal” values used for **PROCESS CONTROL** when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

\*\* The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of **ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

<b>Attributes</b>	Product will be free of foreign material contamination, rips, holes, and tears.
<b>Labeling</b>	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
<b>Certification</b>	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.