



# RADOX® 155

Multi core cable – screened



- Excellent high and low temperature and ozone resistance
- Weatherproof
- Flame retardant
- Soldering resistant
- Flexible
- Easy to strip

## Application

Permanent installation indoor and outdoor for the connection of fixed and loose parts.

## Composition of cable

① Core:	
Conductor	stranded tin plated copper, acc. to EN 60228, class 5
Insulation	RADOX 155 extruded and electron beam crosslinked polyolefin copolymer
Core colours	2 up to 5 core acc. to CENELEC HD 308 (see page 127) 6 core and more: black numbered with yellow/green earthing other colours on request
② Fillers (optional)	RADOX 125
③ Separator (optional)	plastic tape
④ Screen	copper braid, optical coverage: ≥ 85 %
⑤ Separator (optional)	plastic tape
⑥ Sheath	RADOX 155 extruded and electron beam crosslinked polyolefin copolymer
Colour	black

## Technical data

Voltage rating $U_0/U$	< 0.75 mm <sup>2</sup>	450/750 V AC
Test voltage	< 0.75 mm <sup>2</sup>	2500 V AC
Voltage rating $U_0/U$	≥ 0.75 mm <sup>2</sup>	600/1000 V AC
Test voltage	≥ 0.75 mm <sup>2</sup>	3500 V AC
Temperature range	fixed	-55 up to +155 °C
Min. operating temperature	flexible	-40 °C
Max. conductor temperature	at short circuit (max. 5 s)	+280 °C
Min. bending radius	fixed	4 × cable-dia.
	flexible	5 × cable-dia.

## Fire tests

Flame propagation:		
Vertical of a single cable	EN 50265-2-1, IEC 60332-1	
Vertical of bunched cables	DIN EN 50266-2-5	category D

# RADOX® 155

Multi core cable – screened

Extract from our delivery programme

Cross section n × mm <sup>2</sup>	Conductor			Core	Screen	Cable	Weight
	Construction nom. n × mm dia.	Dia. max. mm	R <sub>20</sub> IEC 60228 max. Ω/km	Dia. mm	Dia. mm	Dia. mm	nom. kg/100 m
2 × 0.25	19 × 0.12	0.61	88.5	1.45 ± 0.05	3.35	5.1 ± 0.3	3.43
6 × 0.25	19 × 0.12	0.61	88.5	1.45 ± 0.05	5.07	6.95 ± 0.15	6.71
4 × 2 × 0.25	19 × 0.12	0.61	88.5	1.45 ± 0.05	11.2	14.0 ± 0.4	27.7
4 × 0.5	19 × 0.18	0.9	40.1	1.71 ± 0.10	5.55	7.6 ± 0.15	7.62
16 × 0.5	19 × 0.18	0.9	40.1	1.71 ± 0.10	9.0	11.6 ± 0.4	20.3
3 G 1.5	30 × 0.25	1.61	13.3	2.73 ± 0.10	6.6	8.7 ± 0.3	11.6
10 G 1.5	30 × 0.25	1.61	13.3	2.73 ± 0.10	11.9	14.7 ± 0.4	33.2
26 G 1.5	30 × 0.25	1.61	13.3	2.73 ± 0.10	18.0	22.0 ± 0.5	74.1
8 G 2.5	50 × 0.25	2.06	8.6	3.5 ± 0.10	14.5	17.9 ± 0.5	49.8
9 G 2.5	50 × 0.25	2.06	8.6	3.5 ± 0.10	15.1	18.6 ± 0.5	51.8

Other cross sections on request.