

## 1. GENERAL DESCRIPTION

---

Long-term outdoor and indoor corrosion inhibitor.

CRC SP 400 II is a long-term, outdoor and indoor corrosion inhibitor for machined surfaces and assemblies subjected to long periods of storage or adverse shipping conditions. The amber, dry, waxy film never becomes brittle and is highly resistant to humidity and severe corrosive atmospheres.

## 2. FEATURES

---

- Long-term protection (up to 2 years outdoors) for all metals during shipment or extended storage.
- Waxy film seals out moisture effectively. Highly resistant to humidity and salt spray.
- Can be removed or diluted, for film thickness variation, with petroleum solvents.
- Aerosols use hydrocarbon propellant for controlled application and film thickness.

## 3. APPLICATIONS

---


- Protection of finished components, in-process parts, in-transit goods, raw materials, structural steel.
- Effective corrosion shield for overseas shipments, 'winterizing' of farm machinery, outdoor storage.
- Protection of equipment, tools, dies, molds, jigs, pipes, shafts, housings, wire ropes, valves, gears.
- To be used for brine and chloride resistance in refrigeration plants.
- In paper and pulp plants.
- As a cable end sealer and pipe joint protector in utilities.
- Protection of air conditioning and electrical equipment in hospitals and educational institutions.
- In airport and aircraft maintenance and construction.
- Approved by DGA – Technical Act 0329-10/DT/ASA/PFA of 12 April 2010.

## 4. DIRECTIONS

---

- Shake aerosol can well before use. Stir or mix bulk product to break its paraffin structure before dipping or brushing applications.
- Mask area not to be treated. If necessary, remove by solvent cleaners (CRC Fast Dry Degreaser, CRC Industrial Degreaser...).
- Film thickness may be adjusted by thinning with petroleum solvents, but corrosion resistance varies with film thickness (see typical properties).
- For applications in wet or very humid conditions, CRC 3-36 should be applied first for complete moisture displacement. Allow then 2 to 4 hours for solvent evaporation before SP 400 is applied.
- When finished spraying, clean aerosol valve by turning can upside down and pressing actuator until only propellant escapes.
- Do not use on energized equipment. Use in well ventilated areas.





**A safety data sheet (MSDS) according to EC Regulation N°1907/2006 Art.31 and amendments is available for all CRC products.**

### 5. TYPICAL PRODUCT DATA (without propellant)

---

Appearance	: amber, waxy
Specific gravity (@ 20°C)	
aerosol	: 0.87
bulk	: 0.87
Flash point (closed cup)	
aerosol	: < 0°C
bulk	: 40°C
Dynamic viscosity (@ 20°C)	
bulk	: 150 to 1600 mPa.s depending on paraffin structure
Coverage	
spraying	: 20 m <sup>2</sup> /L
dipping	: 5 m <sup>2</sup> /L
Solvent dissipation (@ 20°C, thin film)	: 1-2 h.
Film properties (after evaporation of solvent)	
Film appearance	: dry, waxy
Film thickness	: 10 - 50 µm
Salt spray resistance (*) (ASTM B 117)	
@ 10 µm film thickness	: 200 h.
@ 50 µm film thickness	: > 500 h.
Flow resistance (vertical)	: > 80°C

### 6. PACKAGING

---

aerosol :	12 x 300 ml
bulk :	4 x 5 l ; 2 x 20 l ; 1 x 200 l

\* Typical corrosion protection results will depend mainly on surface conditions and environment. It may be up to 1 year outdoors or more than 2 years indoors. The first application therefore should be checked periodically for signs of corrosion. Once the time of protection under any specific condition is determined, CRC SP400 may be re-applied at intervals to maintain protection.

All statements in this publication are based on service experience and/or laboratory testing. Because of the wide variety of equipment and conditions and the unpredictable human factors involved, we recommend that our products be tested on-the-job prior to use. All information is given in good faith but without warranty neither expressed nor implied.

This Technical Data Sheet may already have been revised at this moment for reason such as legislation, availability of components and newly acquired experiences. The latest and only valid version of this Technical Data Sheet will be sent to you upon simple request or can be found on our website: [www.crcind.com](http://www.crcind.com).

We recommend you to register on this website for this product so you will be able to receive any future updated version automatically.

Version : 10053 03 0908 1  
Date : 30 November 2010



Manufactured by :  
CRC Industries Europe BVBA  
Touwslagerstraat 1 – 9240 Zele – Belgium  
Tel (32) (0) 52/45.60.11 Fax (32) (0) 52/45.00.34  
[www.crcind.com](http://www.crcind.com)

